

Product Data Sheet

GMA ExtremeBlast™ (GMX 36 #)



Average Chemical Composition (Typical)		
SiO ₂ *	35%
Al ₂ O ₃	19%
FeO	15%
Fe ₂ O ₃	19%
MgO	7%
CaO	3%
TiO ₂	1%
MnO	1%

*Refers to SiO₂ bound within the lattice of the homogeneous garnet crystal (not free silica).

Product Range (typical weight % retained)			
Mesh	Microns	Cumulative	Discrete
18	1000	3	3
20	850	7	4
25	710	18	11
30	600	30	12
35	500	39	9
40	425	47	8
45	355	49	2
50	300	53	4
60	250	67	14
70	212	89	22
80	180	99	10
100	150	100	1
PAN	PAN	100	0

Other Characteristics (Typical)	
Radioactivity	Non-detectable above background
Moisture Absorption	Non-hygroscopic, Inert
Total Chlorides	1 – 3 ppm
Conductivity	90 μS/cm (9 mS/m)

*Tested in accordance to ISO and ASTM standards.

Mineral Composition (Typical)		
Garnet (predominately Almandine)	>92%
Pyroxene	3%
Ilmenite	<1%
Quartz (free silica)	<0.3%
Hornblende	<3.5%
Other	0.3%

Physical Characteristics (Typical)	
Bulk Density	143.58lbs/ft ³ (2.3 t/m ³)
Specific Gravity	4.1
Hardness (moh)	7.5 – 8.0
Melting Point	2282°F (1250°C)
Shape of Natural Grains	Sub-angular to Angular

- Packaging**
- 55 lb. (25 kg) paper bags on 1 metric ton or 2 metric ton pallet
 - 1 metric ton or 2 metric ton bulk bags with bottom spout and an inner plastic liner
 - Loose bulk delivered by pneumatic truck.
- Source**
- Made in USA from imported raw materials
 - Product code: GMAX-USA-GX3
 - Product specification: GX3 Garnet.

PDS Code: GMAX-USA-GX3 PDS-V1-2018-08